

Sizes		Specs	
Standards / Value	FACE BRICK C216	FBX	
	THIN BRICK C1088	TBX	
	THIN BRICK PCI	Length and Height	
Size			
Avg. Comp. (PSI)	18,676		
Avg. 24 Hr. Cold Water Absor.	4.33		
Avg. 5 Hr. Boil Absor.	5.99		
Avg. Saturation Coeff.	0.72		
Avg. Initial Rate Absor.	7.90		
Test Report	 Download		
Size	Thin		
Avg. 24 Hr. Cold Water Absor.	2.60		
Avg. 5 Hr. Boil Absor.	3.85		
Avg. Saturation Coeff.	0.68		