

Standards / Value	FACE BRICK C216	FBX
	THIN BRICK C1088	TBX

Size	
Avg. Comp. (PSI)	15,323
Avg. 24 Hr. Cold Water Absor.	4.12
Avg. 5 Hr. Boil Absor.	5.16
Avg. Saturation Coeff.	0.80
Avg. Initial Rate Absor.	9.30
Test Report	 Download
Size	Thin
Avg. 24 Hr. Cold Water Absor.	4.12
Avg. 5 Hr. Boil Absor.	5.16
Avg. Saturation Coeff.	0.80
Test Report	 Download

Cleaning Recommendation

Belden Brick recommends using **Vanatrol®** to clean this product. Alternatively, **EaCo Chem NMD 80®** can be used to clean any of our brick.