

Burlesque Glazed Series
Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in²)	Core Volume (%)
Bermuda Blue Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Black Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Cardinal Red Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Cloud Grey Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
White Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
White with Speck Glazed		Modular	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots.
U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.0	525	6.86

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

Burlesque Glazed Series – Thin Brick
Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in²)	Core Volume (%)
Bermuda Blue Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
Black Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
Cardinal Red Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
Cloud Grey Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
White Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
White with Speck Glazed Thin Brick		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

[illegible]

Note: Products are also available as Full Brick, see Full Brick Technical Data Sheet.